

Nameplates /
Barcode Labels


Service Diagrams /
Schematics

Machine
Control Panels

THE TECHNOLOGY:

ANODIZED LAYER

The glass-clear, sapphire-hard anodized layer resists chemicals, paint, abrasion and dirt.



SEALED IMAGE

The image is absorbed into the pores.

ALUMINUM LAYER

The rigid aluminum base won't peel, crack or delaminate.

EXCEPTIONALLY DURABLE. WIDELY SPECIFIED. ALWAYS READABLE.

For over 50 years, industrial and military engineers have specified Metalphoto photosensitive anodized aluminum for durable nameplates, barcode labels, service schematics and control panels installed in harsh operating environments. Metalphoto's proprietary technology permanently seals a UV-stable image inside of anodized aluminum, offering the **confidence of unparalleled durability, image resolution and barcode readability.**

Specified by Nordic Air (HDT Global), a leading manufacturer of military-grade mobile HVAC systems, Metalphoto nameplates, service schematics and control panels are designed to withstand installation in harsh military and industrial operating environments. Metalphoto is also specified for mobile flightline air-conditioning, shipboard cooling systems and mobile power generation.

Metalphoto of Cincinnati has been a leading full-service manufacturer of durable custom identification products for more than 50 years. Contact MPC for the best solution to your equipment identification needs.

PRODUCT BENEFITS

EXCEPTIONALLY DURABLE:

- + UV-stable image is permanently sealed within the anodized aluminum.
- + Virtually impervious to chemicals, heat, abrasion, salt spray and sunlight.
- + Certified for 20 year plus outdoor applications.
- + Earned more top scores than any other IUID barcode label material tested by the U.S. Navy (NSWC, Corona Division, IUID Center; August 2011).

WIDELY SPECIFIED:

- + Meets a wide array of commercial, government and military specifications.
- + Notable certifications include: MIL-STD-130N, STANAG 2290, GGP-455B(3) Type I, MIL-DTL-15024F, MIL-P-19834B and A-A-50271 (several others listed on metalphoto.com).

PHOTOGRAPHIC RESOLUTION:

- + Photographic image affords extreme detail and contrast at any size.
- + Anti-counterfeit security printing is available.



UV STABLE



ABRASION
RESISTANT



TEMPERATURE
RESISTANT



FLUID
RESISTANT



RECYCLABLE

PERFORMANCE CHARACTERISTICS

Because of its ability to perform across a range of challenging environments, Metalphoto meets an array of government, industrial and military specifications. Visit www.metalphoto.com for a list of specifications for which Metalphoto is qualified.

CHARACTERISTIC	RESULT
Abrasion Resistance	No pronounced image loss, degradation or reduced readability after 7,000 cycles on an abrading wheel.
Acid Corrosion	No deterioration or image degradation after 24 hours in 3% nitric acid.
Heat Resistance	No legibility loss or degradation when subjected to 1,000°F.
Salt Spray Corrosion	No deleterious effect after a 720-hr salt spray (fog) test. 2,6 "Very Good" corrosion resistance after 113 days seawater exposure.
Accelerated Light and Weather Resistance	No pronounced deterioration of legibility after 400-hr carbon arc weatherometer exposure. (≈ 20+ year outdoor life)
Accelerated Oxygen Aging	No discoloration or fading after 96-hr/300 psi/ 70°C oxygen bomb aging
Stain Resistance	No black fading when plates are exposed to tincture of iodine.
Cleaning Resistance	No deleterious effects when tested with alkaline cleaners (MILC- 87937 or equivalent) for aircraft surfaces.
Low Temperature Resistance	No deleterious effect or image fade after 1 hour at -50°F. No impairment of legibility upon exposure at -67°F.
Organic Solvent Resistance	No softening, staining or noticeable fade after 24-hr exposure to: JP-4 fuel, Gasoline, Mineral Spirits, Methyl Ethyl Ketone, Turpentine, Turbine & Jet Fuel, Kerosene, Xylol, Acetone, Toluol, Heptane, Trichlorethylene, MIL-H-5606 Hydraulic Fluid and MIL-L-7808 Jet Engine Oil.
Fungus Resistance	Visual reading of "0" per ASTM-G21.
Thermal Shock	No deterioration after 3 cycles between -65°C and 125°C
Moisture Resistance	No deterioration after 10 humidity cycles per MIL-STD-202, method 106.

TECHNICAL SPECIFICATIONS

MATERIAL: Anodized Aluminum

SIZES: Up to 24" x 40"

THICKNESSES: .003", .005", .008", .012", .020", .032", .039", .063", .090", .125"

FINISHES:



MATTE
non-reflective
with dull finish



SATIN
semi-gloss medium
reflective material



4
brushed to resemble
a stainless steel finish



GLOSS
highly reflective,
mirror-like

CONTACT MPC

Call **1-800-528-4058** or visit our website at **MPofCinci.com**

*Metalphoto of Cincinnati does not warrant the performance of its materials in any environment.
Metalphoto is a registered trademark of Horizons Incorporated.

Ver. 1.2 MAY 2013



Metalphoto of Cincinnati

1080 Skillman Drive
Cincinnati, OH 45215

T: 1-800-482-7758
F: 216-475-6507

E: cincics@mpofcinci.com
www.mpofcinci.com